

MIDWEST FASTENER CD STUD LOAD STRENGTHS

<i>STUD MATERIAL</i>	<i>STUD SIZE</i>	<i>MAXIMUM FASTENING TORQUE (Inch Lbs.)*</i>	<i>ULTIMATE TENSILE LOAD (Lbs.)</i>	<i>MAXIMUM SHEAR LOAD (Lbs.)</i>
LOW-CARBON, COPPER-FLASHED STEEL	6-32	6	500	375
	8-32	12	765	575
	10-24	14	960	720
	1/4-20	43	1750	1300
	5/16-18	72	2900	2200
	3/8-16	106	4300	3250
STAINLESS STEEL 304	6-32	10	790	590
	8-32	20	1260	940
	10-24	23	1530	1150
	1/4-20	75	2880	2160
	5/16-18	126	3750	5350
	3/8-16	185	4850	7150
ALUMINUM ALLOY 1100	6-32	2.5	200	125
	8-32	5	295	185
	10-24	6.5	380	235
	1/4-20	21.5	670	415
	5/16-18	36	1125	695
	3/8-16	53	1660	1000
ALUMINUM ALLOY 6061	6-32	6.5	350	160
	8-32	13	560	229
	10-24	19	670	310
	1/4-20	40	1240	679
	5/16-18	70.5	2025	1210
	3/8-16	100	2985	1750
BRASS 70-30 (260) 65-35 (268)	6-32	8	600	390
	8-32	16	860	560
	10-24	18.5	1040	680
	1/4-20	61	1950	1275
	5/16-18	102	3280	2140
	3/8-16	150	4800	3160

*These values should develop fastener tension to slightly less than yield point.



450 Richard St.
 Miamisburg, OH 45342
 Toll Free: 800-852-8352
 Fax: 937-866-4174